



Standard Practice for Ultimate Analysis of Coal and Coke¹

This standard is issued under the fixed designation D3176; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers the term ultimate analysis as it is applied to the analysis of coal and coke. The information derived is intended for the general utilization by applicable industries, to provide the basis for evaluation, beneficiation, or for other purposes.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- D346 Practice for Collection and Preparation of Coke Samples for Laboratory Analysis
- D2013 Practice for Preparing Coal Samples for Analysis
- D2234/D2234M Practice for Collection of a Gross Sample of Coal
- D3172 Practice for Proximate Analysis of Coal and Coke
- D3173 Test Method for Moisture in the Analysis Sample of Coal and Coke
- D3174 Test Method for Ash in the Analysis Sample of Coal and Coke from Coal
- D3177 Test Methods for Total Sulfur in the Analysis Sample of Coal and Coke
- D3178 Test Methods for Carbon and Hydrogen in the Analysis Sample of Coal and Coke³

¹ This practice is under the jurisdiction of ASTM Committee D05 on Coal and Coke and is the direct responsibility of Subcommittee D05.21 on Methods of Analysis.

Current edition approved Nov. 1, 2009. Published December 2009. Originally approved in 1974. Last previous edition approved in 2002 as D3176–89(2002). DOI: 10.1520/D3176-09.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Withdrawn. The last approved version of this historical standard is referenced on www.astm.org.

- D3179 Test Methods for Nitrogen in the Analysis Sample of Coal and Coke³
- D3302 Test Method for Total Moisture in Coal
- D4239 Test Methods for Sulfur in the Analysis Sample of Coal and Coke Using High-Temperature Tube Furnace Combustion Methods
- D4596 Practice for Collection of Channel Samples of Coal in a Mine
- D4916 Practice for Mechanical Auger Sampling³
- D5142 Test Methods for Proximate Analysis of the Analysis Sample of Coal and Coke by Instrumental Procedures
- D5192 Practice for Collection of Coal Samples from Core
- D5373 Test Methods for Instrumental Determination of Carbon, Hydrogen, and Nitrogen in Laboratory Samples of Coal and Coke
- D6609 Guide for Part-Stream Sampling of Coal
- D6883 Practice for Manual Sampling of Stationary Coal from Railroad Cars, Barges, Trucks, or Stockpiles
- D7256/D7256M Practice for Mechanical Collection and Within-System Preparation of a Gross Sample of Coal from Moving Streams³

3. Terminology

3.1 Definitions:

3.1.1 *ultimate analysis*—in the case of coal and coke, the determination of carbon and hydrogen in the material, as found in the gaseous products of its complete combustion, the determination of sulfur, nitrogen, and ash in the material as a whole, and the calculation of oxygen by difference.

NOTE 1—Moisture is not by definition a part of the ultimate analysis of coal or coke but must be determined in order that analytical data may be converted to bases other than that of the analysis sample.

NOTE 2—Inasmuch as some coals contain mineral carbonates, and practically all contain clay or shale containing combined water, a part of the carbon, hydrogen, and oxygen found in the products of combustion may arise from these mineral components.

4. Significance and Use

4.1 Summarizing the ash content and the content of the organic constituents in a specific format under the heading, *Ultimate Analysis*, provides a convenient and uniform system for comparing coals or cokes. This tabulation used with that of *Proximate Analysis* (Practice D3172) permits cursory valuation

of coals for use as fuel or in other carbonaceous processes and of cokes for metallurgical purpose.

5. General Requirements

5.1 Coal sample collection shall be in accordance with any of the following Guides or Practices as appropriate: **D2234/D2234M**, **D6609**, **D4596**, **D4916**, **D5192**, and **D6883**

5.2 For coal, sample preparations shall be in accordance with Practice **D2013** or **D7256/D7256M**. The analysis sample shall be the material pulverized to pass a 250- μm (No. 60) sieve in accordance with Practice **D2013**.

5.3 Coke sampling and preparation shall be in accordance with Practice **D346**.

6. Specific Requirements

6.1 *Carbon and Hydrogen*—The carbon and hydrogen determination shall be made in accord with Test Methods **D3178** or **D5373**.

6.2 *Sulfur*—The sulfur determination shall be made in accordance with Test Methods **D3177** or **D4239**.

6.3 *Nitrogen*—The nitrogen determination shall be made in accordance with Test Methods **D3179** or **D5373**.

6.4 *Ash*—The ash determination shall be made in accordance with Test Method **D3174** or Test Methods **D5142**.

6.5 *Oxygen*—There being no satisfactory direct ASTM test method for determining oxygen, it shall be calculated by subtracting from 100 the sum of the other components of the ultimate analysis. The result so obtained is affected by errors incurred in the other determinations of the ultimate analysis

and also by the changes in weight of the ash-forming constituents on ignition. By definition, oxygen calculated as a weight percentage of the analysis sample according to this procedure does not include oxygen in the mineral matter or in the ash, but does include oxygen in the free water (moisture) associated with the analysis sample. See Section 7 of this practice for calculating and reporting results on other bases.

6.6 *Moisture*—The moisture determination shall be made in accordance with Test Method **D3173** or Test Methods **D5142**.

6.7 The aire-dry loss or total moisture determination shall be made in accordance with Practice **D3302**.

7. Calculation and Report

7.1 The results of an ultimate analysis may be reported on any of a number of bases, differing from each other in the manner by which moisture is treated.

7.2 To avoid ambiguity and provide a means for conversion of data to bases other than the reported basis, it is essential that except for data reported on a dry basis, an appropriate moisture content be given in the data report.

7.3 It is recommended that, for data reported on the as-received basis (or any other moist basis), a footnote or some other means be used in the report to indicate whether the hydrogen and oxygen values reported do or do not include the hydrogen and oxygen in the free water (moisture) associated with the sample.

7.4 Procedures for converting ultimate analysis sample data to other bases are presented in **Table 1**.

TABLE 1 Procedures for Converting As-Determined Values to Other Bases^A

Reporting Basis Parameter ^B	As-Determined ^C	Dry	As-Received ^{D,E}	
			<i>H_{ar}</i> and <i>Ox_{ar}</i> Include <i>H</i> and <i>Ox</i> in Moisture (<i>M_{ar}</i>)	<i>H_{ar}</i> and <i>Ox_{ar}</i> Do Not Include <i>H</i> and <i>Ox</i> as <i>M_{ar}</i>
Ash	No corrections (See standard method)	$P_d = P_{ad} \times \left(\frac{100}{100 - M_{ad}} \right)$	$P_{ar} = P_{ad} \times \left(\frac{100 - M_{ar}}{100 - M_{ad}} \right)$	same as column at left
Carbon				
Nitrogen (<i>P</i>)				
Sulfur				
Hydrogen (<i>H</i>)	No corrections (See standard method)	$H_d = (H_{ad} - 0.1119M_{ad}) \times \left(\frac{100}{100 - M_{ad}} \right)$	$H_{ar} = [(H_{ad} - 0.1119M_{ad}) \times \left(\frac{100 - M_{ar}}{100 - M_{ad}} \right) + 0.1119M_{ar}]$	$H_{ar} = (H_{ad} - 0.1119M_{ad}) \times \left(\frac{100 - M_{ar}}{100 - M_{ad}} \right)$
Oxygen (<i>Ox</i>)	$Ox_{ad} = 100 - A_{ad} - C_{ad} - H_{ad} - N_{ad} - S_{ad}$	$Ox_d = (Ox_{ad} - 0.8881M_{ad}) \times \left(\frac{100}{100 - M_{ad}} \right)$ or $Ox_d = 100 - A_d - C_d - H_d - N_d - S_d$	$Ox_{ar} = [(Ox_{ad} - 0.8881M_{ad}) \times \left(\frac{100 - M_{ar}}{100 - M_{ad}} \right) + 0.8881M_{ar}]$	$Ox_{ar} = (Ox_{ad} - 0.8881M_{ad}) \times \left(\frac{100 - M_{ar}}{100 - M_{ad}} \right)$

^AA = ash, weight %;

M = moisture, weight %;

P = a symbol used interchangeably in the table to refer to ash, or carbon, or nitrogen, or sulfur, weight %;

H = hydrogen, weight %;

Ox = oxygen, weight %;

ad = as-determined from analysis sample;

ar = as received or any other moisture-containing basis (that is, equilibrium capacity moisture basis, as-shipped moisture basis, bed moisture basis) if the appropriate moisture value is substituted for *M_{ar}* in the formulae; and

d = dry basis.

^BAll parameters expressed on a weight percent basis.

^CHydrogen and oxygen reported on as-determined basis include hydrogen and oxygen in free moisture associated with analysis sample.

^DAlternative procedures are shown, differing on the basis of whether hydrogen and oxygen in the moisture are included or are not included in the report values. A footnote or other means should be employed to indicate the basis used.

^ETo convert results to a moisture-containing basis other than as-received, as for example, equilibrium capacity moisture, substitute the appropriate moisture value for *M_{ar}* in the equations.

TABLE 2 Ultimate Analysis Data

Test Parameter	As-Determined		As-Received Basis	
	Hydrogen and Oxygen Include <i>H</i> and <i>Ox</i> in Sample Moisture (M_{ad})	Dry Basis	Hydrogen and Oxygen Include <i>H</i> and <i>Ox</i> in Sample Moisture (M_{ar})	Hydrogen and Oxygen Do Not Include <i>H</i> and <i>Ox</i> in Sample Moisture (M_{ar})
Carbon, weight %	60.08	66.02	46.86	46.86
Hydrogen, weight %	5.44	4.87	6.70	3.46
Nitrogen, weight %	0.88	0.97	0.69	0.69
Sulfur, weight %	0.73	0.80	0.57	0.57
Ash, weight %	7.86	8.64	6.13	6.13
Oxygen, weight % (by difference)	25.01	18.70	39.05	13.27
Total %	100.00	100.00	100.00	70.98
Total moisture, weight % (as-received)	...		(29.02)	29.02
Moisture weight % (samples as-determined)	9.00			Total % 100.00

(Air-dry loss in accordance with Test Method D3302 = 22.00 %)

7.4.1 Hydrogen and oxygen on the as-determined basis include hydrogen and oxygen in free water (moisture) associated with the analysis sample. However, hydrogen and oxygen values reported on other moisture-containing bases may be reported either as containing or as not containing the hydrogen and oxygen in water (moisture) reported on that basis. Alternative conversion procedures are shown in Table 1.

7.5 An example of ultimate analysis data tabulated for a hypothetical coal on various bases is given in Table 2.

8. Precision

8.1 The permissible differences between two or more determinations shall not exceed the values listed in the precision section of the specific test method for the parameter determined.

9. Keywords

9.1 ash; carbon; coal; coke; hydrogen; nitrogen; oxygen; sulfur; ultimate analysis

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).